



Lliça Packagin Slu
 Carretera Sabadell a
 Granollers Km 11,1
 08185 Lliça de Vall (Spain)

TEL :
France +33 (0) 1 46 35 12 37
 (Cadex)
Spain: +34 934 759 100 (Careo
 Iberica)
 email: info@llissapackaging.com

Lliça Blanco

Folding Box Board GC1

Carton couché GC1

Specification	unit	Tolerances	300	325	350	400	440
Caliper / Epaisseur	µm	± 5%	440	485	530	610	690
Stiffness/ Rigidité (Taber-ST)	mN.m	± 15%	7,6	9,7	12,3	18,8	25,3
Stiffness (Taber- SM)	mN.m	± 15%	22,1	28,0	33,9	45,7	54,0

Substance / Grammage	g/m²	± 3%	ISO
Bending stiffness / Rigidité	mN.m	± 5%	ISO
Brightness / Blancher	%	± 2	Recto-Verso / Top-Back
COBB 1n	g/m²	± 20	Recto-Verso / Top-Back
Suitability for laser coding	%	100	Aptitude au marquage laser (data matrix)
Suitability for inkjet	%	100	Aptitude au jet d'encre (data matrix)
Robinson test	<1 scale from 0 to 4		

Test Condition:

Temperature 23± 1 C, Relative humidity 50% ± 2